

RUST-OLEUM[®]
INDUSTRIAL



MASONRY MATT

Solvent-free wall paint



- Large-scale project quality
- High financial return
- Easy to apply
- Good hiding power
- Easy to clean

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

MASONRY MATT

DESCRIPTION

Black, matt, solvent-free wall paint based on a synthetic resin dispersion, specifically designed for painting walls and ceilings in large-scale new construction and renovation projects. Can be applied universally in dry and wet rooms. For interior and exterior use.

RECOMMENDED USE

Ideal for project-based use. Suitable surfaces include: existing coats of wall paint, cement and plasterwork, concrete, brick, etc.

RECOMMENDED SYSTEM

General: The surface must be capable of supporting the paint, completely set, clean, dry, and free from dust or grease. Sand and repair surface irregularities. Remove and/or repair all loose and unstable coats. In the case of exterior applications, remove all moss, mould and algal growth.

New, untreated substrates

- Prime (highly) absorbent surfaces in their entirety using Stabilising primer.
- Thoroughly clean powdery surfaces. Prime using Stabilising primer after allowing to dry.
- Apply the top coat after allowing to dry.

Existing intact coats of wall paint

- Clean using Paint cleaner.
- Apply an intermediate coat of Wall primer opaque if necessary.
- Apply the top coat after allowing to dry.

Existing, flaking coats of wall paint

- Remove loose parts.
- Thoroughly wash powdery coats and allow them to dry.
- Carry out any repairs.
- Prime with Stabilising primer.
- Apply the top coat after allowing to dry.

Stains caused by nicotine, damp, rust or soot

- Clean thoroughly using Paint cleaner.
- Treat surface/stain with Sealing primer.
- Apply the top coat after allowing to dry.

The systems described above apply for the most common types of surface. For specific applications and/or detailed advice, please contact Rust-Oleum Europe

TECHNICAL DATA

Density (g/cm ³):	1.33
Gloss Level:	Matt
Gloss level at 85°:	7%
Solids content in volume:	37%

DRY TIMES BY 20° C/RH 50%

Touch dry:	2 h
Dry to recoat:	6 h

RECOMMENDED WET FILM THICKNESS

150 µ

RECOMMENDED DRY FILM THICKNESS

65 µ

THEORETICAL CONSUMPTION

Approx. 7 m²/litre per coat

PRACTICAL CONSUMPTION

The actual coverage depends on the nature and the structure of the surface and the application method.

SURFACE PREPARATION

The surface must be capable of supporting the paint, completely set, clean, dry, and free from dust or grease. Sand and repair surface irregularities. Remove and/or repair all loose and unstable coats. In the case of exterior applications, remove all moss, mould and algal growth.

DIRECTIONS FOR USE

Stir thoroughly prior to use. The first coat can be diluted with a maximum of 10% water. Apply in 1 or 2 coats using a suitable brush, paint roller or paint sprayer. Always work wet-on-wet to prevent visible marks in the paint. Back-roll all overlaps in the same direction. Do not touch up when drying.

APPLICATION CONDITIONS

Do not apply at temperatures below +8°C. Only apply if the surface temperature is at least 3°C above the dew point temperature. Do not apply outdoors when it is likely to rain, when frost is expected or in direct sunlight. Always use the required personal protective equipment when applying this product. Do not inhale spray mist/fumes given off by products. Always ventilate appropriately when applying.

APPLICATION & THINNING: AIRLESS SPRAY

Nozzle: 0.017-0.021"
Pressure: >200 bars
Dilute: 0-10%

The stated settings for spraying this product should be taken as your starting point. Depending on the on-site conditions, the settings will have to be determined by the person applying the paint.

CLEANING OF EQUIPMENT / SPILLS

Water and soap

SAFETY DATA

VOC level:	5 g/l
VOC category:	A/a
VOC limit:	30 g/l
Remarks regarding safety:	Surplus product: This paint and the packaging should be disposed of at a collection point for hazardous or special waste.

SHELF LIFE

Minimum of 12 months in the tightly sealed original packaging in a dry, cool and frost-free place.

Date issued: 20/03/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu