

RUST-OLEUM®
INDUSTRIAL



PREMIUM COVER SATIN

Wall paint with excellent hiding power



- Excellent coverage
- Easy to clean
- Satin

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

PREMIUM COVER SATIN

DESCRIPTION

Wall paint offering excellent hiding power based on synthetic resin dispersion. A single coat is generally sufficient, saving time and the cost of an extra coat. Low-odour, breathable and easy to clean. Designed specifically to provide a long-lasting finish to interior walls and ceilings. For interior use.

RECOMMENDED USE

Suitable surfaces include: existing coats of wall paint, cement and plasterwork, concrete, brick, gypsum panelling, board, etc. Also suitable for painting glass fibre fabric.

RECOMMENDED SYSTEM

General: The surface must be capable of supporting the paint, completely set, clean, dry, and free of dust or grease. Repair cracks and surface irregularities. Remove and/or repair all loose and unstable coats.

New, untreated substrates

- Prime (highly) absorbent surfaces in their entirety using Fixator.
- Thoroughly clean powdery surfaces. Prime using Fixator after allowing to dry.
- Apply the top coat after allowing to dry.

Existing intact coats of wall paint

- Clean.
- Apply an intermediate coat of Premium Cover if necessary.
- Apply the top coat after allowing to dry.

Existing, non-load-bearing coats of wall paint

- Remove loose parts.
- Thoroughly wash powdery coats and allow them to dry.
- Carry out any repairs.
- Prime with Fixator.
- Apply the top coat after allowing to dry.

Contamination caused by nicotine, damp, rust or soot- Clean thoroughly.

- Treat surface/stain with Insulator.

The systems described above apply for the most common types of surface. For specific applications and/or detailed advice, please contact Rust-Oleum Europe.

TECHNICAL DATA

Density (g/cm ³):	1.2
Gloss Level:	Satin
Gloss level at 60°:	20-30%
Solids content in volume:	45%

DRY TIMES BY 20° C/RH 50%

Touch dry:	2 h
Dry to recoat:	4-6 h

RECOMMENDED WET FILM THICKNESS

111 µ

RECOMMENDED DRY FILM THICKNESS

50 µ

THEORETICAL CONSUMPTION

Approx. 9 m²/litre per coat

PRACTICAL CONSUMPTION

The actual coverage depends on the nature and the structure of the surface and the application method.

SURFACE PREPARATION

The surface must be capable of supporting the paint, completely set, clean, dry, and free of dust or grease. Repair cracks and surface irregularities. Remove and/or repair all loose and unstable coats.

DIRECTIONS FOR USE

Stir thoroughly prior to use. The first coat can be diluted with a maximum of 10% water. Apply in 1 or 2 coats using a suitable brush, paint roller or paint sprayer. Always work wet-on-wet to prevent marks in the paint. Back-roll all overlaps in the same direction. Do not touch up when drying.

APPLICATION CONDITIONS

Do not apply at temperatures below +8°C. Only apply if the surface temperature is at least 3°C above the dew point temperature. Always use the required personal protective equipment when applying this product. Do not inhale spray mist/fumes given off by products. Always ventilate appropriately when applying.

APPLICATION & THINNING: AIRLESS SPRAY

Nozzle: 0.017-0.21
Pressure: approx. 200 bars
Dilute: 0-10%

The stated settings for spraying this product should be taken as your starting point. Depending on the on-site conditions, the settings will have to be determined by the person applying the paint.

APPLICATION & THINNING: AIR-ATOMISED SPRAY

Nozzle: 0.017-0.21
Pressure: approx. 120 bars
Air pressure: approx. 2 bars
Dilute: 0-10%

The stated settings for spraying this product should be taken as your starting point. Depending on the on-site conditions, the settings will have to be determined by the person applying the paint.

CLEANING OF EQUIPMENT / SPILLS

Water and soap

SAFETY DATA

VOC level:	30 g/l
VOC category:	A/b
VOC limit:	100 g/l
Remarks regarding safety:	Surplus product: This product and the packaging should be disposed of at a collection point for hazardous or special waste.

SHELF LIFE

Minimum of 12 months in the tightly sealed original packaging in a dry, cool and frost-free place.

Date issued: 20/03/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu