

**RUST-OLEUM®**  
INDUSTRIAL



## ULTRA SCRUBBABLE MATT

# Multi-purpose matt wall paint



- Scrub-resistant, Class 1 (DIN EN 13300)
- Good coverage
- Virtually odour-free
- For interior use and protected exterior surfaces
- Matt

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# ULTRA SCRUBBABLE MATT

## DESCRIPTION

Multi-purpose matt wall paint based on an acrylic dispersion. Scrub-resistant, Class 1. Easily applicable and good coverage. Particularly suitable for painting walls and ceilings in large-scale new construction and renovation projects. For interior use and protected exterior surfaces.

## RECOMMENDED USE

Suitable surfaces include: existing coats of wall paint, cement and plasterwork, concrete, brick, gypsum panelling, board, etc. Also suitable for painting glass fibre fabric.

## RECOMMENDED SYSTEM

General: The surface must be capable of supporting the paint, completely set, clean, dry, and free from dust or grease. Sand and repair surface irregularities. Remove and/or repair all loose and unstable coats. In the case of exterior applications, remove all moss, mould and algal growth.

### New, untreated substrates

- Prime highly absorbent surfaces in their entirety using Stabilising primer.
- Thoroughly clean powdery surfaces. Prime using Stabilising primer after allowing to dry.
- Paint to cover after allowing to dry.

### Existing intact coats of wall paint

- Clean using Paint cleaner.
- Apply an intermediate coat of Wall Primer Opaque if necessary.
- Apply the top coat after allowing to dry.

### Existing, non-load-bearing coats of wall paint

- Remove loose parts.
- Thoroughly wash powdery coats and allow them to dry.
- Carry out any repairs.
- Prime with Stabilising primer.
- Apply the top coat after allowing to dry.

### Contamination caused by nicotine, damp, rust or soot

- Clean thoroughly using Paint cleaner.
- Treat surface/stain with Sealing primer.
- Apply the top coat after allowing to dry.

The systems described above apply for the most common types of surface. For specific applications and/or detailed advice, please contact Rust-Oleum Europe.

## TECHNICAL DATA

Density (g/cm <sup>3</sup> ):	1.45
Gloss Level:	Matt
Gloss level at 85°:	<5%
Solids content in volume:	40%

## DRY TIMES BY 20° C/RH 50%

Touch dry:	2 h
Dry to recoat:	4 h

## RECOMMENDED WET FILM THICKNESS

125 µ

## RECOMMENDED DRY FILM THICKNESS

50 µ

## THEORETICAL CONSUMPTION

Approx. 8 m<sup>2</sup>/l per coat

## PRACTICAL CONSUMPTION

The actual coverage depends on the nature and the structure of the surface and the application method.

## SURFACE PREPARATION

The surface must be capable of supporting the paint, completely set, clean, dry, and free from dust or grease. Sand and repair surface irregularities. Remove and/or repair all loose and unstable coats. In the case of exterior applications, remove all moss, mould and algal growth.

## DIRECTIONS FOR USE

Stir thoroughly prior to use. The first coat can be diluted with a maximum of 10% water. Apply in 1 or 2 coats using a suitable brush, paint roller or paint sprayer. Always work wet-on-wet to prevent visible brush strokes. Back-roll all overlaps in the same direction. Do not touch up when drying.

## APPLICATION CONDITIONS

Do not apply at temperatures below 8°C. Only apply if the surface temperature is at least 3°C above the dew point temperature. Do not apply outdoors when it is likely to rain, when frost is expected or in direct sunlight. Always use the required personal protective equipment when applying this product. Do not inhale spray mist/fumes given off by products. Always ventilate appropriately when applying.

## APPLICATION & THINNING: AIRLESS SPRAY

Nozzle: 0.015-0.017"  
Pressure: approx. 180 bars

The stated settings for spraying this product should be taken as your starting point. Depending on the on-site conditions, the settings will have to be determined by the person applying the paint.

## APPLICATION & THINNING: AIR-ATOMISED SPRAY

Nozzle: 0.015-0.017"  
Pressure: approx. 175 bars  
Air pressure: 0.5-1 bar

The stated settings for spraying this product should be taken as your starting point. Depending on the on-site conditions, the settings will have to be determined by the person applying the paint.

## CLEANING OF EQUIPMENT / SPILLS

Water (and soap)

## REMARKS

Roller marks are more likely to happen with dark colors due to the absorption of light which highlights surface defects. To prevent this, prefer application by spraying.

Date issued: 20/03/2025

**Available colours & pack sizes:** Please refer to the respective product page on [www.rust-oleum.eu](http://www.rust-oleum.eu) for an overview of actual available colours and pack sizes.

**Disclaimer:** The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from [www.rust-oleum.eu](http://www.rust-oleum.eu) or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
info@rust-oleum.eu

# ULTRA SCRUBBABLE MATT

## SAFETY DATA

VOC level:	30 g/l
VOC category:	A/a
VOC limit:	30 g/l
Remarks regarding safety:	Surplus product: This paint and the packaging should be disposed of at a collection point for hazardous or special waste.

## SHELF LIFE

Minimum of 12 months in the tightly sealed original packaging in a dry, cool and frost-free place.

Date issued: 20/03/2025

**Available colours & pack sizes:** Please refer to the respective product page on [www.rust-oleum.eu](http://www.rust-oleum.eu) for an overview of actual available colours and pack sizes.

**Disclaimer:** The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from [www.rust-oleum.eu](http://www.rust-oleum.eu) or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)