

RUST-OLEUM®
INDUSTRIAL



ULTRA SCRUBBABLE MATT

Multi-purpose matt wall paint



- Scrub-resistant, Class 1 (DIN EN 13300)
- Good coverage
- Virtually odour-free
- For interior use and protected exterior surfaces
- Matt

LE SAVOIR-FAIRE EN PROTECTION™

WWW.RUST-OLEUM.EU

ULTRA SCRUBBABLE MATT

DESCRIPTION

Multi-purpose matt wall paint based on an acrylic dispersion. Scrub-resistant, Class 1. Easily applicable and good coverage. Particularly suitable for painting walls and ceilings in large-scale new construction and renovation projects. For interior use and protected exterior surfaces.

UTILISATION RECOMMANDÉE

Suitable surfaces include: existing coats of wall paint, cement and plasterwork, concrete, brick, gypsum panelling, board, etc. Also suitable for painting glass fibre fabric.

SYSTÈME RECOMMANDÉ

General: The surface must be capable of supporting the paint, completely set, clean, dry, and free from dust or grease. Sand and repair surface irregularities. Remove and/or repair all loose and unstable coats. In the case of exterior applications, remove all moss, mould and algal growth.

New, untreated substrates

- Prime highly absorbent surfaces in their entirety using Stabilising primer.
- Thoroughly clean powdery surfaces. Prime using Stabilising primer after allowing to dry.
- Paint to cover after allowing to dry.

Existing intact coats of wall paint

- Clean using Paint cleaner.
- Apply an intermediate coat of Wall Primer Opaque if necessary.
- Apply the top coat after allowing to dry.

Existing, non-load-bearing coats of wall paint

- Remove loose parts.
- Thoroughly wash powdery coats and allow them to dry.
- Carry out any repairs.
- Prime with Stabilising primer.
- Apply the top coat after allowing to dry.

Contamination caused by nicotine, damp, rust or soot

- Clean thoroughly using Paint cleaner.
- Treat surface/stain with Sealing primer.
- Apply the top coat after allowing to dry.

The systems described above apply for the most common types of surface. For specific applications and/or detailed advice, please contact Rust-Oleum Europe.

DONNÉES TECHNIQUES

Densité (g/cm ³):	1.45
Niveau de brillance:	Mat
Niveau de brillance à 85°:	<5%
Extrait sec en volume:	40%

TEMPS DE SÉCHAGE À 20°C/HR 50%

Au toucher:	2 h
Recouvrable:	4 h

EPAISSEUR DE FILM HUMIDE RECOMMANDÉE

125 µ

EPAISSEUR DE FILM SEC RECOMMANDÉE

50 µ

CONSOMMATION THÉORIQUE

Approx. 8 m²/l per coat

CONSOMMATION PRATIQUE

The actual coverage depends on the nature and the structure of the surface and the application method.

PRÉPARATION DE SURFACE

The surface must be capable of supporting the paint, completely set, clean, dry, and free from dust or grease. Sand and repair surface irregularities. Remove and/or repair all loose and unstable coats. In the case of exterior applications, remove all moss, mould and algal growth.

PRÉCAUTIONS D'UTILISATION

Stir thoroughly prior to use. The first coat can be diluted with a maximum of 10% water. Apply in 1 or 2 coats using a suitable brush, paint roller or paint sprayer. Always work wet-on-wet to prevent visible brush strokes. Back-roll all overlaps in the same direction. Do not touch up when drying.

CONDITIONS D'APPLICATION

Do not apply at temperatures below 8°C. Only apply if the surface temperature is at least 3°C above the dew point temperature. Do not apply outdoors when it is likely to rain, when frost is expected or in direct sunlight. Always use the required personal protective equipment when applying this product. Do not inhale spray mist/fumes given off by products. Always ventilate appropriately when applying.

APPLICATION & DILUTION: PISTOLET AIRLESS

Nozzle: 0.015-0.017"
Pressure: approx. 180 bars

The stated settings for spraying this product should be taken as your starting point. Depending on the on-site conditions, the settings will have to be determined by the person applying the paint.

APPLICATION & DILUTION: PISTOLET PNEUMATIQUE

Nozzle: 0.015-0.017"
Pressure: approx. 175 bars
Air pressure: 0.5-1 bar

The stated settings for spraying this product should be taken as your starting point. Depending on the on-site conditions, the settings will have to be determined by the person applying the paint.

NETTOYAGE DU MATERIEL / ECLABOUSSURES

Water (and soap)

REMARQUES

Le risque éventuel de reprise est plus important avec les teintes foncées du fait de l'absorption de la lumière qui souligne les défauts. Pour éviter ce risque, préférer une application au pistolet.

Date d'émission: 20/03/2025

Couleurs et conditionnements disponibles: Reportez-vous à la page produit concernée sur www.rust-oleum.eu pour avoir un aperçu des couleurs et des tailles d'emballage actuellement disponibles.

Notion de responsabilité: Les informations communiquées ici sont véridiques et exactes et sont fournies de bonne foi au meilleur de nos connaissances, mais sans garantie. Il est estimé que l'utilisateur se sera assuré lui-même de la compatibilité de nos produits avec son usage particulier. Rust-Oleum Europe ne sera en aucun cas tenue pour responsable quant aux dommages consécutifs ou indirects. Les produits doivent être stockés, manipulés et appliqués conformément aux conditions respectant les recommandations de Rust-Oleum Europe détaillées dans le dernier exemplaire de la fiche technique du produit. Il incombe aux utilisateurs de veiller à disposer de l'exemplaire actuel. Les dernières versions de la fiche technique du produit sont disponibles gratuitement et peuvent être téléchargées sur www.rust-oleum.eu ou sur demande adressée à notre département Service à la clientèle. Rust-Oleum Europe se réserve le droit de modifier les propriétés de ses produits sans avis préalable.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu

ULTRA SCRUBBABLE MATT

DONNÉES DE SÉCURITÉ

Teneur en COV:	30 g/l
Catégorie COV:	A/a
Limite COV:	30 g/l
Remarques pour la sécurité:	Surplus product: This paint and the packaging should be disposed of at a collection point for hazardous or special waste.

DURÉE DE VIE

12 mois minimum dans l'emballage d'origine bien fermé, et entreposé dans un endroit sec et frais, à l'abri du gel.

Date d'émission: 20/03/2025

Couleurs et conditionnements disponibles: Reportez-vous à la page produit concernée sur www.rust-oleum.eu pour avoir un aperçu des couleurs et des tailles d'emballage actuellement disponibles.

Notion de responsabilité: Les informations communiquées ici sont véridiques et exactes et sont fournies de bonne foi au meilleur de nos connaissances, mais sans garantie. Il est estimé que l'utilisateur se sera assuré lui-même de la compatibilité de nos produits avec son usage particulier. Rust-Oleum Europe ne sera en aucun cas tenue pour responsable quant aux dommages consécutifs ou indirects. Les produits doivent être stockés, manipulés et appliqués conformément aux conditions respectant les recommandations de Rust-Oleum Europe détaillées dans le dernier exemplaire de la fiche technique du produit. Il incombe aux utilisateurs de veiller à disposer de l'exemplaire actuel. Les dernières versions de la fiche technique du produit sont disponibles gratuitement et peuvent être téléchargées sur www.rust-oleum.eu ou sur demande adressée à notre département Service à la clientèle. Rust-Oleum Europe se réserve le droit de modifier les propriétés de ses produits sans avis préalable.

Rust-Oleum Netherlands B.V.

Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)

Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.

38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.

Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu