RUST-OLEUM®
INDUSTRIAL

## SPEED PATCH POURABLE GRADE

# Quick setting, pourable repair product.

- Accepts heavy traffic 2 hours after application
- Easy to prepare: add water and mix
- Possible to apply on slightly wet concrete
- Sets at low temperatures (5 °C)
- For deep or shallow repairs

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# SPEED PATCH POURABLE GRADE

## BESKRIVELSE
Speed Patch Pourable is an easy to mix pourable material for quick repairs to level concrete, inside or outside. NOTE: This product is only available in the UK.

## ANBEFALET BRUG
Repairs of heavily trafficked floors.

## TEKNISK DATA

| | |
|---|---|
| Trykstyrke: | 45 MN/m² |
| Blandingsforhold: | Powder : Water = 3 : 1 (Volume) |

## TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

| | |
|---|---|
| Håndteringstør: | 2 h |
| Fuldt hærdet: | 24 h |
| Brugstid: | 5 - 10 min |

## TEORETISK FORBRUG
As a guide, each unit of 25 kg will cover approximately 0.5 m² at 25 mm thick.

## PRAKTISK FORBRUG
Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## FORBEHANDLING AF OVERFLADEN
The substrate should be clean and free from oil or contaminants. Any loose material should be removed from the surface. If possible wire brush the surface. Edges of the repair should be cut to depth to avoid feather-edging in heavy wear areas. Speed Patch Pourable can be applied to damp (not wet) concrete.

## BRUGSANVISNING
Remove the bag of powder from the plastic bucket and use the empty bucket or other suitable container for mixing. Due to the short working life of the mixed product, we recommend you carry out the mixing near to the repair, not near to the water source. It's also useful to have a bucket of water nearby, so you can quickly immerse and clean the tools after use. Put the water into the empty bucket or container and gradually add the powder stirring constantly to achieve a pourable slurry. For small quantities mix by hand using a flat bladed tool such as a spatula, and for larger quantities use a mixer fitted into a slow speed electric drill. Do not add excessive water or drying time will be extended and the performance may be impaired. As the mixture hardens quickly, pour the Speed Patch Pourable into the hole to be repaired immediately. We do not recommend re-stirring as this could potentially weaken the final repair.

## ANVENDELSESBETINGELSER
Apply at a temperature of approximately 5ºC - 20ºC. Do not apply at less than 5ºC.

## PÅFØRING OG FORTYNDING: RIVE/MURSKE
When a smooth consistency is achieved, simply pour Speed Patch in to the hole. If the product has been properly mixed it will self-level and will need minimal trowelling. Speed Patch Pourable can be applied in any depth between 5 mm and 100 mm. Repairs in lightly trafficked areas can be feather edged, but thin edges are not recommended for medium or heavily trafficked repairs.

## RENGØRING AF UDSTYR/SPILD
Remove excess with a cloth or scraper and wash with water before the product sets.

## BEMÆRKNINGER
Temperatures below 10°C will delay the curing process. As a guide, allow 24 hours when applied at 5°C. Do not apply at temperatures below 0°C. Speed Patch Pourable can be applied at any depth between 5 - 100 mm and repairs can be feather edged in light traffic areas. When mixed, this product will be pourable so is not suitable for repairs to sloping floors or exposed edges. After curing the product can be painted with any suitable floor paint. If the floor being repaired is very rough, you may wish to screed the whole floor for a smooth flat surface before painting.

## HOLDBARHED
Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

**Udstedelsesdato:** 22/11/2023

**Tilgængelige farver og pakningsstørrelser:** Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

**Ansvarsfraskrivelse:** Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

**Rust-Oleum Netherlands B.V.**
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu