

**RUST-OLEUM**<sup>®</sup>  
— INDUSTRIAL —



## SPEED PATCH POURABLE GRADE

# Quick setting, pourable repair product.

- Accepts heavy traffic 2 hours after application
- Easy to prepare: add water and mix
- Possible to apply on slightly wet concrete
- Sets at low temperatures (5 °C)
- For deep or shallow repairs



LE SAVOIR-FAIRE EN PROTECTION™

[WWW.RUST-OLEUM.EU](http://WWW.RUST-OLEUM.EU)



# SPEED PATCH POURABLE GRADE

## DESCRIPTION

Speed Patch Pourable is an easy to mix pourable material for quick repairs to level concrete, inside or outside. NOTE: This product is only available in the UK.

## UTILISATION RECOMMANDÉE

Repairs of heavily trafficked floors.

## DONNÉES TECHNIQUES

Résistance compression: 45 MN/m<sup>2</sup>  
Ratio de mélange: Powder : Water = 3 : 1 (Volume)

## TEMPS DE SÉCHAGE À 20°C/HR 50%

Manipulable: 2 h  
Dur à cœur: 24 h  
Pot-life (vie du mélange): 5 - 10 min

## CONSUMMATION THÉORIQUE

As a guide, each unit of 25 kg will cover approximately 0.5 m<sup>2</sup> at 25 mm thick.

## CONSUMMATION PRATIQUE

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PRÉPARATION DE SURFACE

The substrate should be clean and free from oil or contaminants. Any loose material should be removed from the surface. If possible wire brush the surface. Edges of the repair should be cut to depth to avoid feather-edging in heavy wear areas. Speed Patch Pourable can be applied to damp (not wet) concrete.

## PRÉCAUTIONS D'UTILISATION

Remove the bag of powder from the plastic bucket and use the empty bucket or other suitable container for mixing. Due to the short working life of the mixed product, we recommend you carry out the mixing near to the repair, not near to the water source. It's also useful to have a bucket of water nearby, so you can quickly immerse and clean the tools after use. Put the water into the empty bucket or container and gradually add the powder stirring constantly to achieve a pourable slurry. For small quantities mix by hand using a flat bladed tool such as a spatula, and for larger quantities use a mixer fitted into a slow speed electric drill. Do not add excessive water or drying time will be extended and the performance may be impaired. As the mixture hardens quickly, pour the Speed Patch Pourable into the hole to be repaired immediately. We do not recommend re-stirring as this could potentially weaken the final repair.

## CONDITIONS D'APPLICATION

Apply at a temperature of approximately 5°C - 20°C. Do not apply at less than 5°C.

## APPLICATION & DILUTION: RACLETTE/TRUELLE

When a smooth consistency is achieved, simply pour Speed Patch in to the hole. If the product has been properly mixed it will self-level and will need minimal trowelling. Speed Patch Pourable can be applied in any depth between 5 mm and 100 mm. Repairs in lightly trafficked areas can be feather edged, but thin edges are not recommended for medium or heavily trafficked repairs.

## NETTOYAGE DU MATERIEL / ECLABOUSSURES

Remove excess with a cloth or scraper and wash with water before the product sets.

## REMARQUES

Temperatures below 10°C will delay the curing process. As a guide, allow 24 hours when

applied at 5°C. Do not apply at temperatures below 0°C. Speed Patch Pourable can be applied at any depth between 5 - 100 mm and repairs can be feather edged in light traffic areas. When mixed, this product will be pourable so is not suitable for repairs to sloping floors or exposed edges. After curing the product can be painted with any suitable floor paint. If the floor being repaired is very rough, you may wish to screed the whole floor for a smooth flat surface before painting.

## DURÉE DE VIE

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date d'émission: 22/11/2023

**Couleurs et conditionnements disponibles:** Reportez-vous à la page produit concernée sur [www.rust-oleum.eu](http://www.rust-oleum.eu) pour avoir un aperçu des couleurs et des tailles d'emballage actuellement disponibles.

**Notion de responsabilité:** Les informations communiquées ici sont véridiques et exactes et sont fournies de bonne foi au meilleur de nos connaissances, mais sans garantie. Il est estimé que l'utilisateur se sera assuré lui-même de la compatibilité de nos produits avec son usage particulier. Rust-Oleum Europe ne sera en aucun cas tenue pour responsable quant aux dommages consécutifs ou indirects. Les produits doivent être stockés, manipulés et appliqués conformément aux conditions respectant les recommandations de Rust-Oleum Europe détaillées dans le dernier exemplaire de la fiche technique du produit. Il incombe aux utilisateurs de veiller à disposer de l'exemplaire actuel. Les dernières versions de la fiche technique du produit sont disponibles gratuitement et peuvent être téléchargées sur [www.rust-oleum.eu](http://www.rust-oleum.eu) ou sur demande adressée à notre département Service à la clientèle. Rust-Oleum Europe se réserve le droit de modifier les propriétés de ses produits sans avis préalable.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu