

**RUST-OLEUM®**  
INDUSTRIAL



## SPEED PATCH POURABLE GRADE

# Quick setting, pourable repair product.

- Accepts heavy traffic 2 hours after application
- Easy to prepare: add water and mix
- Possible to apply on slightly wet concrete
- Sets at low temperatures (5 °C)
- For deep or shallow repairs



KNOW-HOW TO PROTECT™

[WWW.RUST-OLEUM.EU](http://WWW.RUST-OLEUM.EU)

# SPEED PATCH POURABLE GRADE

## DESCRIZIONE

Speed Patch Pourable is an easy to mix pourable material for quick repairs to level concrete, inside or outside. NOTE: This product is only available in the UK.

## UTILIZZO CONSIGLIATO

Repairs of heavily trafficked floors.

## DATI TECNICI

Resistenza alla compressione: 45 MN/m<sup>2</sup>  
Rapporto di miscelazione: Powder : Water = 3 : 1 (Volume)

## TEMPI DI ASCIUGATURA A 20°C/UR 50%

Asciutto da maneggiare: 2 h  
Completamente indurito: 24 h  
Durata del contenitore: 5 - 10 min

## CONSUMO TEORICO

As a guide, each unit of 25 kg will cover approximately 0.5 m<sup>2</sup> at 25 mm thick.

## CONSUMO PRATICO

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PREPARAZIONE DELLA SUPERFICIE

The substrate should be clean and free from oil or contaminants. Any loose material should be removed from the surface. If possible wire brush the surface. Edges of the repair should be cut to depth to avoid feather-edging in heavy wear areas. Speed Patch Pourable can be applied to damp (not wet) concrete.

## ISTRUZIONI PER L'USO

Remove the bag of powder from the plastic bucket and use the empty bucket or other suitable container for mixing. Due to the short working life of the mixed product, we recommend you carry out the mixing near to the repair, not near to the water source. It's also useful to have a bucket of water nearby, so you can quickly immerse and clean the tools after use. Put the water into the empty bucket or container and gradually add the powder stirring constantly to achieve a pourable slurry. For small quantities mix by hand using a flat bladed tool such as a spatula, and for larger quantities use a mixer fitted into a slow speed electric drill. Do not add excessive water or drying time will be extended and the performance may be impaired. As the mixture hardens quickly, pour the Speed Patch Pourable into the hole to be repaired immediately. We do not recommend re-stirring as this could potentially weaken the final repair.

## CONDIZIONI DI APPLICAZIONE

Apply at a temperature of approximately 5°C - 20°C. Do not apply at less than 5°C.

## APPLICAZIONE E DILUIZIONE: RASTRELLO/PALETTA

When a smooth consistency is achieved, simply pour Speed Patch in to the hole. If the product has been properly mixed it will self-level and will need minimal trowelling. Speed Patch Pourable can be applied in any depth between 5 mm and 100 mm. Repairs in lightly trafficked areas can be feather edged, but thin edges are not recommended for medium or heavily trafficked repairs.

## PULITURA DELLE ATTREZZATURE / DEGLI SVERSAMENTI

Remove excess with a cloth or scraper and wash with water before the product sets.

## NOTE

Temperatures below 10°C will delay the curing process. As a guide, allow 24 hours when applied at 5°C. Do not apply at temperatures below 0°C. Speed Patch Pourable can be applied at any depth between 5 - 100 mm and repairs can be feather edged in light traffic areas. When mixed, this product will be pourable so is not suitable for repairs to sloping floors or exposed edges. After curing the product can be painted with any suitable floor paint. If the floor being repaired is very rough, you may wish to screed the whole floor for a smooth flat surface before painting.

## SCADENZA

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Data del rilascio: 13/05/2025

**Colori e formati di confezione disponibili:** Si prega di consultare la pagina relativa al prodotto su [www.rust-oleum.eu](http://www.rust-oleum.eu) per una visione complessiva dei colori e dei formati di confezione effettivamente disponibili.

**Dichiarazione di non responsabilità:** Le informazioni contenute nel presente documento sono al meglio della nostra conoscenza, vere e accurate e sono fornite in buona fede ma senza garanzia. L'utente sarà ritenuto soddisfatto/a indipendentemente dall'idoneità dei nostri prodotti per il suo proprio scopo particolare. In nessun caso Rust-Oleum Europe potrà essere ritenuta responsabile per danni consequenziali o incidentali. I prodotti devono essere conservati, maneggiati e applicati in condizioni conformi alle raccomandazioni dettagliate di Rust-Oleum Europe contenute nella copia più recente della scheda tecnica del prodotto. È responsabilità dell'utente accertarsi di disporre della copia attuale. Le copie più recenti della scheda tecnica del prodotto sono disponibili gratuitamente e scaricabili da [www.rust-oleum.eu](http://www.rust-oleum.eu) o a fronte di richiesta al nostro servizio clienti. Rust-Oleum Europe si riserva il diritto di modificare le proprietà dei suoi prodotti senza alcun preavviso.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu