





# **Easy to apply 1 component anti-slip floor coating**

- For foot traffic, interior and exterior
- Anti-slip additive is premixed in the coating
- For use on old concrete (>2yrs), metal and wood
- · Touch dry after 6 hours

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

# SUPERGRIP® 1K ANTI-SLIP FLOOR COATING

#### DESCRIPTION

Easy to apply solvent based Alkyd anti-slip floor coating specially designed for applying on old (>2 years), dry concrete for interior and exterior use. The coating has a good resistance against abrasion and neutral detergents (no alkaline cleaning agents) and is resistance during short contact periods against lubricating oils, fuel, petrol etc.

# RECOMMENDED USE

7100 Floor Coating can be applied on concrete floors older than 2 years, which are completely clean and dry. It is not recommended to apply on smooth/dense concrete or concrete containing a damp repellent additive, which will prevent a good adhesion. 7100 Floor Coating can also be applied on old good adhering coatings. 7100 can be applied onto metal floors which have been correctly prepared and primed with a suitable Rust-Oleum metal primer.

# **TECHNICAL DATA**

Density (g/cm³): 1,0 -1,1 Gloss Level: Gloss Solids content in volume: 36 - 40%

# DRY TIMES BY 20° C/RH 50%

Touch dry: 6 hours
Dry to recoat: 24 hours
Fully cured: 1 week

# RECOMMENDED WET FILM THICKNESS

130 um

# RECOMMENDED DRY FILM THICKNESS

50 µm

# THEORETICAL CONSUMPTION

8,0 m<sup>2</sup>/l at 50 µm dry

# PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

# **SURFACE PREPARATION**

Remove oil, grease and other contaminations with Rust-Oleum 2901 EpoxyShield Cleaner/Degreaser for floors or high pressure- (steam) cleaning in combination with appropriate detergents. Sand old intact coatings to roughen the surface in order to establish a good adhesion. Check the compatibility with old intact coatings. During application the surface should be dry and clean. On porous concrete a first coat should be applied with 7100 diluted with  $\pm 10\%$  volume 7301. Remove curing compounds by means of dust free blasting.

# **DIRECTIONS FOR USE**

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

# APPLICATION CONDITIONS

Apply in a dry and well-ventilated area.

# **APPLICATION & THINNING: BRUSH**

Sparingly, if required, with 10% volume 7301.

# **APPLICATION & THINNING: ROLLER**

Sparingly, if required, with 10% volume 7301. In case of roller application it can be necessary to apply 2 coats in order to obtain the recommended film thickness.

# **CLEANING OF EQUIPMENT / SPILLS**

Immediately after application using 7301

# REMARKS

Apply 7100 Floor Coating never on alkaline substrates.

Not suitable for use on tiles and in wet areas such as bathrooms.

#### SAFETY DATA

 VOC level:
 456 g/l

 VOC readymix:
 485 g/l

 VOC category:
 A/i

 VOC limit:
 500 g/l

Remarks regarding safety: Consult Safety Data Sheet and Safety Information

printed on the can.

#### SHELF LIFE

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

**Date issued:** 13/05/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V. Zilverenberg 16 5234 GM 's-Hertogenbosch The Netherlands T:+31 (0) 165 593 636 F:+31 (0) 165 593 600

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147

Rust-Oleum France S.A.S 38, av. du Gros Chêne 95322 Herblay France T: +33(0) 130 40 00 44 F: +33(0) 130 40 99 80 N.V. Martin Mathys S.A. Kolenbergstraat 23 3545 Zelem Belgium T: +32 (0) 13 460 200 F: +32 (0) 13 460 201 info@rust-oleum.eu

