

RUST-OLEUM®
— INDUSTRIAL —



SUPERGRIP® TREADSAFE

Anti-slip epoxy floor coating.

- Applicable until 0 °C
- Tough, long lasting finish
- One coat application
- External and internal use

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

SUPERGRIP® TREADSAFE

BESKRIVELSE

Anti-slip epoxy floor coating. 2-Pack epoxy floor coating for concrete and stone.

ANBEFALET BRUG

Treadsafe is ideal for use on floors, stairs, ramps, loading bays and boat decks etc. It can be applied on concrete floors, which are completely clean and dry. It is not recommended to apply on smooth/dense concrete or concrete containing a curing compound, which will prevent a good adhesion.

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Håndteringstør:	24 hours
Fuldt hærdet:	7 days
Brugstid:	Approximately 30 minutes to 1 hour at a temperature of 20°C when decanted into a shallow tray. Pot life will be reduced if the mixed components are left in the mixing tin.

TEORETISK FORBRUG

Rust-Oleum Treadsafe is supplied in a pack designed to cover 5m². Comprises epoxy resin, hardener and anti-slip aggregate.

FORBEHANDLING AF OVERFLADEN

Surfaces to be treated must be at least four weeks old, completely dry and free of surface laitance (a weak dusty layer on concrete), contaminants and any previous poorly bonded coatings. Very smooth concrete or concrete with surface laitance should be etched with a etchant to ensure adequate adhesion. Other surfaces should be dry and free of all loose surface material, contaminants and rust.

BRUGSANVISNING

Pour the liquid contents of the two small tins (resin and hardener) into the larger outer tin and mix thoroughly until uniform in colour. Do not mix in the anti-slip aggregate. The mixed components should be decanted into a shallow tray and be used immediately. (If they are not decanted the components and mixing tin will become quite hot and unusable).

ANVENDELSESBETINGELSER

Store Treadsafe at a temperature range of 15°C - 25°C for 8 hours prior to use. This will ensure easier application of the mixed resin and hardener and maximise pot life.

PÅFØRING OG FORTYNDING: RULLE

A pile-type roller (not foam) should be used to apply the mixture from a shallow roller tray over an area of up to 5m². Immediately sprinkle the anti-slip aggregate uniformly over the wet coat to obtain the desired surface finish (total or light coverage). Using the same roller, roll over the sprinkled aggregate to bed it in and cover it with the mixture. It is not normally necessary to re-charge the roller with mixed resin unless very heavy quantities of grit have been applied.

RENGØRING AF UDSTYR/SPILD

It is not practical to clean applicators and they should be discarded after use. White Spirit or similar solvent will remove accidental splashes (if treated immediately).

BEMÆRKNINGER

To ensure best performance, DO NOT PAINT IF THE FOLLOWING CONDITIONS EXIST: 1) Sealed concrete: dripping a small amount of water onto the surface. If the water beads, a sealer is present and paint may not adhere properly. 2) Moisture in the concrete: apply a sheet of plastic (e.g. garbage bag) to the floor. Tape down the edges and allow to set for 24 hours. If water droplets appear on the inside of the plastic or if concrete appears wet (darker in color), moisture is trapped in the concrete. 3) Loose concrete or concrete dust: if the concrete is loose, chipping or has concrete dust present, the coating will not perform properly unless all loose material and dust is removed and damaged areas are repaired. 4) Floors treated with a levelling mortar or on anhydride floors.

SIKKERHEDSDATA

VOC-niveau:	30 g/l
VOC-færdigblanding:	30 g/l
VOC-kategori:	A/j
Bemærkninger om sikkerhed:	Avoid contact with skin and eyes. For skin contact, wash affected area with soap and water and rinse well. First aid: in case of contact with eyes, flush with cold water for 15 minutes. If swallowed, do not induce vomiting. Drink 1-2 glasses of water or milk. Contact a physician immediately. Keep out of reach of children. Do not take internally. Consult for further information the Safety Data Sheet and the Safety Information printed on the can.

HOLDBARHED

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35° C.

Udstedelsesdato: 09/12/2025

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu