

RUST-OLEUM®
INDUSTRIAL



TARMACOAT™

Versatile rapid curing acrylic floor paint

- Rain-proof and recoatable after just one hour
- Particularly suitable for tarmac, asphalt and bitumen substrates
- Can be applied on slightly damp surfaces
- Excellent resistance to U.V. and weathering
- Water-based formulation, safe to use and virtually no odour

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

TARMACOAT™

DESCRIPTION

Very fast-drying multi-purpose single pack acrylic water-based paint for floors and paint marking.

DOPORUČENÉ POUŽITÍ

As a coating on asphalt, concrete, pavement, bitumen, on parking bays for short term or intermittent use, as line marking, on tennis courts, playgrounds and many more. Not suitable for garage floors. The product will cure sufficiently in approximately 24 hours to accept light traffic (bicycle, car, etc.). In instances where occasional heavy traffic may be expected, allow 48 hours before bringing the area back into service. Cold and damp weather can have a negative effect on drying times.

TECHNICAL DATA

Hustota (g/cm ³):	1,3
Úroveň lesku:	Matt
Úroveň lesku při 60°:	10-12%
Obsah pevných látek v hmotnosti:	57%
Obsah pevných látek v objemu:	45%

DRY TIMES BY 20° C/RH 50%

Dotykem suché:	30 minutes
Suché na manipulaci:	1 hour
Suchý nátěr:	1 hour
Plně vytvrzené:	2 days

DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

120 µm

DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

54 µm

TEORETICKÁ SPOTŘEBA

4 - 8 m² per liter, depending on the type of surface.

PRAKTICKÁ SPOTŘEBA

Depending on the type of surface. On Tarmac, coverage is likely to be close to 4 m²/l.

PŘÍPRAVA POVRCHU

Ensure the surface is clean, sound and dry (slightly damp is acceptable). Tarmaccoat can be applied to existing paint providing all poorly bonded material is removed and glossy surfaces are dulled using abrasive paper. For concrete surfaces which are porous and/or have loose particles or powdering, first prime with Primer 44HS® or EpoxyShield Sealer 5220. For non-porous concrete prime with diluted NOXYDE®. For asphalt surfaces apply first a coat Tarmaccoat™ 20% diluted with water.

NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMÍNKY POUŽITÍ

Do not apply externally if rain or frost is forecast or if the temperature is below 10°C. Relative humidity below 85%.

APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Apply undiluted.

APLIKACE A ŘEDĚNÍ: VÁLEČEK

Apply by medium pile type roller. One coat is generally sufficient although a second coat may be necessary on very porous or very rough surfaces or when a better durable system is required. Apply undiluted.

ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Clean tools in warm soapy water before the product has started to cure.

POZNÁMKY

Do not apply in areas which will be constantly under water.

SAFETY DATA

Úroveň těžkých organických látek:	40 g/l
VOC readymix:	40 g/l
Kategorie VOC:	A/i
Limitní hodnota VOC:	140 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

DOBA POUŽITELNOSTI

Minimum of 2 years from date of production in its sealed original packaging, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 13/05/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu