

RUST-OLEUM®
INDUSTRIAL



TARMACOAT™

Versatile rapid curing acrylic floor paint

- Rain-proof and recoatable after just one hour
- Particularly suitable for tarmac, asphalt and bitumen substrates
- Can be applied on slightly damp surfaces
- Excellent resistance to U.V. and weathering
- Water-based formulation, safe to use and virtually no odour

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

TARMACOAT™

BESKRIVNING

Very fast-drying multi-purpose single pack acrylic water-based paint for floors and paint marking.

REKOMMENDERAD ANVÄNDNING

As a coating on asphalt, concrete, pavement, bitumen, on parking bays for short term or intermittent use, as line marking, on tennis courts, playgrounds and many more. Not suitable for garage floors. The product will cure sufficiently in approximately 24 hours to accept light traffic (bicycle, car, etc.). In instances where occasional heavy traffic may be expected, allow 48 hours before bringing the area back into service. Cold and damp weather can have a negative effect on drying times.

TEKNISK DATA

Densitet:	1,3
Glansnivå:	Matt
Glansnivå vid 60°:	10-12%
Torrsubstansvikt:	57%
Torrsubstansvolym:	45%

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	30 minutes
Hanteringstorr:	1 hour
Torktid:	1 hour
Fullt härdad:	2 days

REKOMMENDERAD VÅTFILMSTJOCKLEK

120 µm

REKOMMENDERAD TORRFILMSTJOCKLEK

54 µm

ÅTGÅNG

4 - 8 m² per liter, depending on the type of surface.

ÅTGÅNG INFORMATION

Depending on the type of surface. On Tarmac, coverage is likely to be close to 4 m²/l.

FÖRBEREDELSE

Ensure the surface is clean, sound and dry (slightly damp is acceptable). Tarmacoat can be applied to existing paint providing all poorly bonded material is removed and glossy surfaces are dulled using abrasive paper. For concrete surfaces which are porous and/or have loose particles or powdering, first prime with Primer 44HS® or EpoxyShield Sealer 5220. For non-porous concrete prime with diluted NOXYDE®. For asphalt surfaces apply first a coat Tarmacoat™ 20% diluted with water.

APPLICERING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICERINGSFÖRHÅLLANDEN

Do not apply externally if rain or frost is forecast or if the temperature is below 10°C. Relative humidity below 85%.

REDSKAP

Apply undiluted.

APPLICERING OCH SPÄDNING: ROLLER

Apply by medium pile type roller. One coat is generally sufficient although a second coat may be necessary on very porous or very rough surfaces or when a better durable system is required. Apply undiluted.

RENGÖRING AV REDSKAP/SPILL

Clean tools in warm soapy water before the product has started to cure.

INFORMATION

Do not apply in areas which will be constantly under water.

SÄKERHETSDATA

VOC-nivå:	40 g/l
VOC färdigmix:	40 g/l
VOC-kategori:	A/i
VOC-gräns:	140 g/l
Anmärkningar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HÅLLBARHET

Minimum of 2 years from date of production in its sealed original packaging, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivningsdatum: 13/05/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdskador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår Kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaper i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu