

RUST-OLEUM®
INDUSTRIAL



PEGACRETE®

Water-based cementitious repair

- Stronger than concrete
- Easy to apply: just add water and stir
- Can be recoated with all paint types
- Low odour
- For indoor and outdoor use



KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

PEGACRETE®

BESKRIVELSE

Powdered repair product for leveling and repairing cracks, holes and other damages in concrete, cement renderings and non-painted brickwork.

ANBEFALET BRUG

For indoor and outdoor works, for levelling and repairing cracks, holes and other damages in concrete, cement renderings and not painted brickwork.

TEKNISK DATA

Tæthed: 1,6
Trykstyrke: 38 MN/m²
Blandingsforhold: Pegacrete : Water = 5kg : 1L

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Genbehandlingstør: 2 days
Fuldt hærdet: 1 month

ANBEFALET VÅDFILM TYKKELSE

2 cm

ANBEFALET TØRFILM TYKKELSE

2 cm

TEORETISK FORBRUG

Maximum 32 kg/m² per layer at 2 cm thickness.

PRAKTISK FORBRUG

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FORBEHANDLING AF OVERFLADEN

On bare substrate: clean with steel brush or sand blaster. The substrate must be solid and free from dust, oil and grease. Porous substrates must be moistened first. Metal parts are to be treated with NOXYDE.

BRUGSANVISNING

Add Pegacrete progressively to water and mix steadily.

ANVENDELSESBETINGELSER

Apply at a temperature of minimum 5°C.

PÅFØRING OG FORTYNDING: RIVE/MURSKER

Filling blade or trowel.

RENGØRING AF Udstyr/SPILD

Water

BEMÆRKNINGER

Do not use more water than necessary for the application. Pegacrete must be applied with a coat thicknesses of 5-20 mm. For thicker coats (20 mm and more) it is preferable to add some sand to the mortar in the following proportion: for 1 litre of mortar, 0,3 till 0,5 litre of sand 0-4 mm.

SIKKERHEDSDATA

VOC-niveau: 0 g/l

: c

Bemærkninger om sikkerhed: Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHED

1 year from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Udstedelsesdato: 12/02/2021

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu